

Data Sheet

Aluminium AlSi10Mg

Alternative Designations

Key Features

EN - 1706

Excellent strength • Good heat crack resistance

Description

This material has excellent strength at elevated temperatures (about 200°C). It has good resistance to corrosion and can be polished easily. It has good workability and good heat crack resistance. The fatigue strength is excellent at 110N/mm². The material has good weldability and is widely applied in parts for vehicles, machines, and aircraft. It has a tensile strength of 450 MPa at room temperature.

Mechanical Properties

| Yield strength | 271 – 297 MPa |
|----------------------|---------------|
| Tensile strength | 450 MPa |
| Elongation at break | 6 - 8% |
| Hardness | 124 |
| Module of elasticity | 73 – 74 GPa |

Physical Properties

| Density | 2.67 g/cm ³ |
|----------------------------------|---------------------------------------|
| Electrical conductivity | $2.1~\text{m}/\Omega\cdot\text{mm}^2$ |
| Coefficient of thermal expansion | on 1.9 – 2.52 _{K-1 · 10-6} |
| Thermal conductivity | 130 – 150 W/m · K |
| Specific heat capacity | 910 – 920 J/kg · K |

Chemical Composition

| Al | Rest is Al | N | - |
|---------------------------|-------------------------------------|---------------------|---------------------------|
| Bi | - | Nb | - |
| С | - | Ni | 0.05% |
| Cd | - | Ο | - |
| Со | - | Р | - |
| Cr | - | Pb | 0.05% |
| Cu | 0.05% | S | - |
| Fe | 0.55% | Si | 9 – 11% |
| Н | - | Sn | 0.05% |
| Mg | 0.25 - 0.45% | Ti | 0.15% |
| Mn | 0.45% | V | - |
| Мо | - | Zn | 0.1% |
| Cu Fe H Mg Mn | 0.05% 0.55% - 0.25 - 0.45% | Si Sn Ti V | 9 – 11% 0.05% 0.15% |

Reference

Datasheets provided by Xometry contain materials sourced through trusted OEMs, material distributors, and databases. Please visit <u>Materialdatacenter.com</u> for further information on this material.