

# Aluminium 5754 / 3.3535 / Al-Mg3

## Alternative Designations

EN AW-5754 / AlMg3 | A-G3M (AFNOR) | AA5754 (AISI/AA) | A95754 (UNS) | 4130 (SIS) | L-3390 (UNE)

## Key Features

Weldability • Corrosion resistance • Non-heat treatable • Suitable for marine applications

## Description

This material has very high mechanical properties when compared to other non-heat treatable aluminum alloys. In addition, it comes with good resistance to atmospheric and seawater corrosion. It has excellent welding characteristics and can be welded using all standard welding methods. It can also be cold formed and forged. It is a non-heat treatable alloy. It can be precipitation hardened to high strength levels by cold working. It has good ductility and formability.

## Mechanical Properties

Yield strength	80 MPa
Tensile strength	180 – 250 MPa
Elongation at break	14 – 16%
Hardness	45
Module of elasticity	70.5 GPa

## Physical Properties

Density	2.66 g/cm <sup>3</sup>
Electrical conductivity	18.797 m/Ω · mm <sup>2</sup>
Coefficient of thermal expansion	23.9 K <sup>-1</sup> · 10 <sup>-6</sup>
Thermal conductivity	140 – 160 W/m · K
Specific heat capacity	900 J/kg · K

## Chemical Composition

Al	Rest is Al	N	-
Bi	-	Nb	-
C	-	Ni	-
Cd	-	O	-
Co	-	P	-
Cr	≤ 0.30%	Pb	-
Cu	≤ 0.10%	S	-
Fe	≤ 0.40%	Si	≤ 0.40%
H	-	Sn	-
Mg	2.6 – 3.6%	Ti	≤ 0.15%
Mn	≤ 0.50%	V	-
Mo	-	Zn	≤ 0.20%

## Reference

Datasheets provided by Xometry contain materials sourced through trusted OEMs, material distributors, and databases. Please visit [Materialdatacenter.com](https://Materialdatacenter.com) for further information on this material.