

Data Sheet

Cobalt chrome / CoCr

Alternative Designations

Key Features

CoCr

Corrosion resistance • Biocompatibility • Wear resistance • Chemically inert

Description

Cobalt Chrome is a high corrosion resistance alloy. The formation of a passive film of Cr203 protects the primary material of this alloy. The mechanical properties are excellent due to increased hardness and tensile strength. This alloy has seen wide applications in the medical and dentistry industries due to its biocompatibility, wear resistance, and chemical inertness. In addition, it is used in the production of wind turbines, cutting tools, and other mechanical parts that require high wear resistance.

Mechanical Properties

Chemical Co	mposition
--------------------	-----------

Yield strength	630 – 840 MPa
Tensile strength	1090 – 1150 MPa
Elongation at break	6 – 15%
Hardness	32
Module of elasticity	170 – 220 GPa

Physical	Properties
i ilysicai	rioperties

Density	8.3 g/cm ³
Electrical conductivity	$0.87~\text{m}/\Omega\cdot\text{mm}^2$
Coefficient of thermal expansion	14 K-1 · 10-6
Thermal conductivity	14 W/m · K
Specific heat capacity	390 J/kg · K

Al	-	Ν	-
Ві	-	Nb	-
С	0.02%	Ni	0.1%
Cd	0.02%	0	-
Со	Rest is Co	Р	-
Cr	28 - 30%	Pb	0.02%
Cu	-	S	-
Fe	0.5%	Si	-
Н	-	Sn	-
Mg	-	Ti	-
Mn	1%	V	-
Мо	5 - 6%	Zn	-

Reference

Datasheets provided by Xometry contain materials sourced through trusted OEMs, material distributors, and databases. Please visit <u>Materialdatacenter.com</u> for further information on this material.